



## SECTION 1: PRODUCT DESCRIPTION

EKOPRODUR S0310/E is a two-component system (POLY+ISO) designed for the production of open-cell polyurethane foam with a semi-rigid self-extinguishing properties.

COMPONENT POLY (polyol mixture): EKOPRODUR S0310/E POLY

COMPONENT ISO (isocyanate): ISO COMPONENT B 1

EKOPRODUR S0310/E is CFC-free, does not include ozone layer depleting foaming agents, according to EU law governing controlled substances - Regulation (EC) No 1005/2009 of the European Parliament and of the Council of 16 September 2009. The system is foamed with carbon dioxide (CO<sub>2</sub>) produced during the reaction of components POLY and ISO.

This polyurethane system has been introduced to the market in accordance with Regulation (EU) No 305/2011 of the European Parliament and of the Council of 9 March 2011, together with an assessment of performance made in accordance with the European harmonized standard EN 14315-1: 2013.

For this product were issued CE marking and Declaration of Performance No. 04DOP-2019-EN and Hygienic Certificate of National Institute of Public Health - National Institute of Hygiene (PZH): BK/B/0429/02/2019

## SECTION 2: APPLICATION

EKOPRODUR S0310/E is designed to perform internal thermal and acoustic insulation of roofs, attics, roofing, ceilings, walls in timber structures, brick, concrete, steel and skeletal systems of residential, industrial as well as public buildings, hangars and media premises by spraying.

**The density of the sprayed foam achieves 8 – 10 kg/m<sup>3</sup> depends on the thickness of the layer and quality of the realization.**

EKOPRODUR S0310/E is processed with the help of specialized high pressure spraying aggregates, equipped with a spray head.

## SECTION 3: COMPONENTS CHARACTERISTICS

### COMPONENT POLY

Formulated polyols mixture in the form of oily liquid, yellow to orange, no suspended particles.

Density at 20°C 1.10 ± 0.02 g/cm<sup>3</sup>

Viscosity at 20°C 280 ± 100 mPa·s



COMPONENT ISO

Mixture of aromatic polyisocyanates, especially diphenylmethane diisocyanate. Brown liquid without suspension.

Density at 20°C	1.22 ± 0.02 g/cm <sup>3</sup>
Viscosity at 20°C	350 ± 100 mPa·s

**SECTION 4: FOAMING CHARACTERISTICS IN LABORATORY CONDITIONS**

Reaction times<sup>1</sup> as well as apparent core density<sup>2</sup> were measured under the laboratory conditions (at 20°C).

Cream time <sup>1</sup>	4 ± 1 sec.
Gel time <sup>1</sup>	10 ± 2 sec.
Tack Free Time <sup>1</sup>	13 ± 3 sec.
Apparent core density	9 ± 1,5 kg/m <sup>3</sup>

**SECTION 5: RECOMMENDED PROCESSING CONDITIONS**

The recommendations are based on experience in applying the foam spray with the machine Graco Reactor H-XP3 with the gun PROBLER P2 ELITE (01 mixing chamber) and Twistork helix mixer.

**IMPORTANT:** Before the use **both**, components must be heated to achieve temperature between 30-40°C. Additionally, you should thoroughly mix Component POLY (around 1 h, by Twistork helix mixer from Graco and also during spraying). Component POLY tends to slow phase separation.

Component ISO does not require mixing.

The volumetric ratio of components POLY : ISO                   **100 : 100**

Temperature settings on the machine:

Heating temperature POLY and ISO:	50-60°C
Heating the hoses:	50-60°C
Components pressure:	80-110 bar (1160-1595 psi)

<sup>1</sup>Reaction times are measured from the beginning of mixing. Cream time – until the moment of rising the reaction mixture’s volume. Gel time – until the moment of drawing out the gelled fibres from the foam. Tack free time – until the moment when the surface of the foam is not sticky. (The procedure according to the internal instructions IJ 11 02).

<sup>2</sup>Apparent core density measured in laboratory conditions.



Components temperature (in drums):	30-40°C
Ambient temperature:	10-35°C
Recommended surface temperature:	15-50°C
Relative ambient humidity:	≤ 70%
Humidity of porous base:	< 15%
Humidity of non-porous base:	0%

Insulated surfaces should be prepared before, should not contain dust, water, oil, loose particles and other substances that could reduce the adhesion of the foam.

Moreover, insulated surfaces should be properly prepared.

Before performing the spraying, the insulated as well as adjacent surfaces such as windows, doors, floors, furniture, etc., should be protected to prevent accidental contamination during spraying - keep in mind that sprayed foam has very good adhesion and can be difficult to remove from the undesired sites.

Pressure setting for Component POLY and the Component ISO should be the same.

Spraying should be performed in such a way that the achieved layers were the thickest (>100mm).

During processing the system please keep in mind all tips and information included in the MSDS sheets for both components.

## SECTION 6: PROPERTIES OF SPRAYED FOAM

The measurements were carried out on foam cut from samples made using a special spraying machine in perfect conditions.

Apparent core density:	≥ 7 kg/m <sup>3</sup>	EN 1602:2013-07
Fire classification:	E	EN 13501-1+A1:2010
	Bs <sub>1</sub> d <sub>0</sub> <sup>3</sup>	EN 13501-1+A1:2010
Short-term water absorption by partial immersion, W <sub>p</sub>	≤ 0.85 kg/m <sup>2</sup>	EN 1609:2013
Thermal conductivity:		EN 12667:2002
	$\lambda_{\text{mean}, i}$	0.037 W/(m·K)
	$\lambda_{90, 90}$	0.038 W/(m·K)
Aged value, $\lambda_D$	0.038 W/(m·K)	EN 12667:2002
Compressive stress at 10%		EN 826:2013-07



relative deformation, $\sigma_{10}$	$\geq 5$ kPa	
Resistance coefficient of water vapour diffusion, $\mu$	3	EN 12086:2013-07
Temperature stability:		EN 1604:2013-07
70°C, 90% RH, after 48 h	$d \leq 4\%$	
	$sz \leq 4\%$	
	$g \leq 1\%$	
-30°C, after 48 h	$d \leq 2\%$	
	$sz \leq 2\%$	
	$g \leq 0.5$	
Adhesion of the foam perpendicularly to the surface:	$\geq 20$ kPa	EN 1607:2013-07
Closed-cell content:	$\leq 3\%$	EN ISO 4590:2005
Mould growth resistance:	growth rate 0	CAUP/ETA no 12/01/21:2007 B

## SECTION 7: PACKAGING

Metal drums with a capacity of 200 dm<sup>3</sup>, IBC with a capacity of 1000 dm<sup>3</sup>.

## SECTION 8: RECOMMENDED STORAGE CONDITIONS

Dry place at 15 - 25°C. Protect from moisture and direct sunlight. Both components should be stored in tightly closed containers. The shelf life in original manufacturer's packaging and stored under normal conditions is **3 MONTHS** from date of manufacture.

## SECTION 9: ADDITIONAL INFORMATION

Data included in this technical information are based on the results from the tests performed in our laboratory as well as on the practical experience. These data do not guarantee the properties of the final product. The results obtained may differ from those listed above especially in the case when the use of the product is under the conditions other than originally intended. As the manufacturer we cannot control the foam is used nor processing parameters, thus the user takes responsibility for proper foam processing and final application. Processing and handling instructions can be found in the technical data sheet (TDS) and safety data sheet (SDS). Failing to meet the manufacturers recommended requirements may adversely affect material processing or foam parameters.

**IMPORTANT:** We are happy to provide technical and substantive assistance in implementing and applying



# TECHNICAL INFORMATION (TDS)

## EKOPRODUR S0310/E

### POLYURETHANE SYSTEM



Date of preparation: 01.02.2016

Update date: 03.02.2021

Version: 3.2/EN

---

*polyurethane system EKOPRODUR S0310/E. At the same time when it is necessary and possible we help in adjusting relevant parameters. In all matters related to the purchase and use of polyurethane system EKOPRODUR S0310/E we encourage you to use a direct contact to our technical and commercial representative or by writing to [prodex@pcc.eu](mailto:prodex@pcc.eu).*